

New Oz Building Materials Group pty Ltd.

TEST REPORT

SCOPE OF WORK

Stonefloor

REPORT NUMBER

251125001SHF-001

TEST DATE(S)

2025-11-25 - 2026-01-05

ORIGINAL ISSUE DATE

2026-01-13


PAGES

6

DOCUMENT CONTROL NUMBER

LFT-APAC-SHF-OP-10k(January 13, 2025)

© 2025 INTERTEK



Test Report

Statement

1. This report is invalid without company's special seal for testing on the assigned page.
2. This report is invalid without an authorized person's signature.
3. This report is invalid if altered.
4. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Don't copy this report in partial without any official approval in writing by our company. This report is invalid without re-stamping the special seal for testing in copying report.
5. This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample(s) tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.
6. Except for the obligation, responsibility and liability (if any) for the appropriateness and professionalism of afore-mentioned testing itself within the scope and amount of the testing fee received, Intertek does not and will not accept any other obligation or liability.
7. If the Client has any questions about the test results, Intertek B&C should be informed within the storage period of the samples. The sample storage period ends 5 working days after the official report issue date. Samples of certification program are retained for the period required by the certification rules. The samples storage period shall be calculated according to the issue date of the original report in the case of quoting results and modifying reports.
8. Intertek B&C will service this report for the entire test record retention period. The test record retention period ends 6 years after this report original issue date. The test record retention period for certification program is 10 years. Test records and other pertinent project documentation will be retained for the entire test record retention period.
9. The report was digital signed by Shang Hai, Intertek Group plc, please using Adobe Acrobat Reader to verify the authenticity.

Test Report

Original Issue Date: 2026-01-13

Intertek Report No. 251125001SHF-001

Applicant: New Oz Building Materials Group pty Ltd.

Address: 2/262 Parramatta Rd Granville NSW 2142 Australia

Attn: Banglan Wang

Test Type: Performance test, samples provided by the applicant.

Product Information

Product Name	Model	Specification
Stonefloor	/	177*1593*8.0mm
Sample ID	Sample Amount	Sample Received Date
S251125001SHF.001	1 pc	2025-11-20
Sample Description		
Thickness: 8mm		

Test Methods And Standards

Test Standard	ISO 846:2019 method A
Specification Standard	ISO 846:2019
Test Conclusion	The samples were tested according to the above standards, and the results are shown in the following page.

Note:

1. This report does not involve sampling. The report only reflects conformity of the tested items of the samples provided by the testing applicant. Representativeness and authenticity of the submitted samples are responsibilities of the testing applicant.

Report Authorized

Name: Flora Fan Name: Tinasay Zheng
 Title: Reviewer Title: Project Engineer


 (1)

Test Report

Original Issue Date: 2026-01-13

Intertek Report No. 251125001SHF-001

Test Items, Method and Results:

Test Item: Fungi resistance test

Test Method: ISO 846:2019 Plastics-Evaluation of the action of microorganisms method A

Test organisms:

Aspergillus niger	ATCC 6275
Penicillium funiculosum	ATCC 36839
Paecilomyces variotii	ATCC 18502
Gliocladium virens	ATCC 9645
Chaetomium globosum	ATCC 6205

Test condition:

Temperature: 29 °C

Relative humidity: 95% R.H.

Duration: 28 days

Assessment of fungal growth

Intensity of growth	Evaluation
0	No growth apparent under the microscope.
1a	No growth visible to the naked eye, but clearly visible under the microscope covering up to 25% of the test surface.
1b	No growth visible to the naked eye, but clearly visible under the microscope covering up to 50% of the test surface.
1c	No growth visible to the naked eye, but clearly visible under the microscope covering more than 50% of the test surface.
2	Growth visible to the naked eye, covering up to 25% of the test surface.
3	Growth visible to the naked eye, covering up to 50% of the test surface.
4	Considerable growth, covering more than 50% of the test surface.
5	Heavy growth, covering the entire test surface.

Test result:

Intensity of growth	Evaluation
0	No growth apparent under the microscope.


Note: Test item was subcontracted on accreditation by CNAS L0823.

Test Report

Original Issue Date: 2026-01-13

Intertek Report No. 251125001SHF-001


Test Photo:



Test Report

Original Issue Date: 2026-01-13

Intertek Report No. 251125001SHF-001

Appendix A: Sample Received Photo**Revision:**

NO.	Date	Changes
251125001SHF-001	2026-01-13	First issue