

## TEST REPORT

No. : XMIN190902311CCM

Date : Dec.03, 2019

Page: 1 of 11

CUSTOMER NAME: NEW OZ BMG AUSTRALIA  
ADDRESS: 262 PARRAMATTA ROAD GRANVILLE 2142 NSW AUSTRALIAN

Sample Name : STONE FLOOR  
Material : Stone powder, Plastic  
Spec. : 8mm


Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

\*\*\*\*\*

Test Required : Selected test(s) as requested by applicant  
SGS Ref. No. : GZIN1909051930MR, XMIN1909006938SC, CANMLC1919083501,  
CANMLC1919082401  
Date of Receipt : Sep.23, 2019  
Testing Start Date : Sep.23, 2019  
Testing End Date : Oct.10, 2019  
Test Result(s) : For further details, please refer to the following page(s)  
(Unless otherwise stated the results shown in this test report refer only to the  
sample(s) tested)

\*\*\*\*\* To be continued\*\*\*\*\*

Signed for  
SGS-CSTC Standards Technical  
Services Co., Ltd. Xiamen Branch  
Testing Center

  
Civi Huang Authorized Signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.  
Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com  
No.31 Xianghong Road, XiangAn Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765380 www.sgs.com.cn  
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765380 e sgs.china@sgs.com

# TEST REPORT

No. : XMIN190902311CCM

Date : Dec.03, 2019

Page: 2 of 11

**Sample Information:**

Flooring, See the photograph(s).

**Test result(s):**

No.	Test item(s)	Test method(s)	Test condition	Test result(s)
1	Dimensional stability (see note 2)	ASTM F2199-18	Specimen: 610mm×177mm×8.0mm, 3pcs Condition: 23±2°C, 50±5%RH, 24h →82±2°C, 360min→ 23±2°C, 50±5%RH, 24h	Average: X Direction: -0.00% Y Direction: -0.01%
2	Curling (see note 3)			Average: Curling value: 0.08mm Curling max: 0.24mm
3	Castor chair test	NALFA LF01-2011 section 3.9	Load: 90kg Type of castors: Type W Cycles: 35000	No visible damage
4	Three-cycle soak test	ANSI/HPVA HP-1- 2009 Section 4.6	Specimen: 127mm×50mm×8.0mm, 6pcs Cycle: 24±3°C, 4h→52°C, 19h Total cycles: 3	No delamination PASS (See annex A)
5	Low temperature dimensional stability (see note 2)	Refer to ASTM F2199-18 and clients' requirement	Condition: 23±2°C, 50±5%RH, 24h →-35°C, 6h→23±2°C, 50±5%RH, 24h (See annex B)	Average: X Direction: -0.01% Y Direction: -0.03%
6	Low temperature curling (see note 3)			Average: Curling value: 0.05mm Curling max: 0.10mm
7	Burning behavior	AS ISO 9239.1: 2003	See annex C	See annex C
8	Water Absorption	ASTM D570-98 (2018)	See annex D	0.05% (See annex D)
9	Soluble heavy metal	ASTM F963-2017	See annex E	Not detected PASS (See annex E)
10	Asbestos content	NIOSH 9002:1994	See annex E	Negative (See annex E)
11	VOCs and Carbonyl Compounds	French Decree 2011-321	See annex F	Class A+ (See annex F)

Note: 1. All test specimens were cut from the samples, see the photograph(s).

2. Dimensional stability, % = (The average final length-The average initial length)/The average initial length ×100.

3. Curling, mm = Dimension after exposure to heat - Dimension before exposure to heat.

4. The test items of 6~11 were carried by SGS-CSTC Standards Technical Services Co., Ltd. Guangzhou Branch.

\*\*\*\*\* To be continued\*\*\*\*\*



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765380 www.sgs.com.cn  
 中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765380 e sgs.china@sgs.com

# TEST REPORT

No. : XMIN190902311CCM

Date : Dec.03, 2019

Page: 3 of 11

## Annex A

Test item: Three-cycle soak test

Test Method: ANSI/HPVA HP-1-2009 Section 4.6

Test condition:

Step1 : submerg in water at temperature 24°C

Duration: 4h

Step 2: dry in oven at temperature 52°C

Duration: 19h

Total cycles: 3

Test Result:

Specimens No.	Delamination	Measure the delamination(mm)			Requirements in ANSI/HPVA HP-1-2009 Section 4.6	Conclusion
		Length	Width	Depth		
1	No	/	/	/	Five of the 6 specimens shall pass the first cycle and 4 of the 6 specimens shall pass the third cycle in 90% of the panels tested.	PASS
2	No	/	/	/		
3	No	/	/	/		
4	No	/	/	/		
5	No	/	/	/		
6	No	/	/	/		

Note: / means no delamination.

\*\*\*\*\* To be continued\*\*\*\*\*



# TEST REPORT

No. : XMIN190902311CCM

Date : Dec.03, 2019

Page: 4 of 11

## Annex B

Test Item: Low temperature dimensional stability and curling

Sample Description: See photo

Test Method: Reference to ASTM F2199-18 and clients' requirement

Test Condition:

23±2°C, 50±5%RH, 24h → -35°C, 6h → 23±2°C, 50±5%RH, 24h

Test Result:

Sample	Test results			
	Length	Width	Curling value	Curling max
A-1	-0.005%	-0.020%	0.05	0.10
A-2	-0.005%	-0.003%		
A-3	-0.008%	-0.079%		
Average	-0.01%	-0.03%		

\*\*\*\*\* To be continued\*\*\*\*\*



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Xiamen Branch Inspection & Testing Services  
Xiamen Branch Testing Center (Commercial Construction Material Laboratory)

No.31 Xianghong Road, XiangAn Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765380 www.sgs.com.cn  
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765380 e sgs.china@sgs.com

# TEST REPORT

No. : XMIN190902311CCM

Date : Dec.03, 2019

Page: 5 of 11

## Annex C

Test item: Determination of the Burning Behavior Using a Radiant Heat Source

Test Method: AS ISO 9239.1:2003

Test condition:

Specimen: 1050 × 230 × 8.0 mm

Flame application time: 10min

Mounting and fixing: Calcium silicate board, with its density about 1016kg/m<sup>3</sup>, thickness about 21.4mm, is as the substrate. The specimens were fixed mechanically to the substrate.

Test result:

Specimen No.	1	2	3	Average
The flame-spread distance at 10min, mm	50	40	40	43
The flame-spread distance at 20min, mm	50	40	40	43
The flame-spread distance at 30min, mm	50	40	40	43
Heat flux at 10 min (HF-10), kW/m <sup>2</sup>	≥11	≥11	≥11	/
Heat flux at 20 min (HF-20), kW/m <sup>2</sup>	≥11	≥11	≥11	/
Heat flux at 30 min (HF-30), kW/m <sup>2</sup>	≥11	≥11	≥11	/
Critical heat flux (CHF), kW/m <sup>2</sup>	≥11	≥11	≥11	/
Integrated smoke value, %-min	292.40	322.36	393.82	336.2

Note:

- Specimens that do not ignite or which spread flame less than 110 mm have a critical heat flux ≥ 11kW/m<sup>2</sup>.
- Observations of the burning characteristics: melting, blistering, charring.

\*\*\*\*\* To be continued\*\*\*\*\*



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.31 Xianghong Road, XiangAn Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765380 www.sgs.com.cn  
 中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765380 e sgs.china@sgs.com

## TEST REPORT

No. : XMIN190902311CCM

Date : Dec.03, 2019

Page: 6 of 11

### Annex D

Test Item: Water Absorption

Sample Description: Floor

Test Method: ASTM D570-98(2018)

Test Condition:

Specimen: 75.8mm×25.4mm×7.8mm

Drying condition: 50±3°C, 24h

Immersion condition: 23±1°C, 24h

Lab Environmental Condition: (23±2)°C, (50±5)%RH


Test Result:

Test Item	Test Result
Water Absorption	0.05%

Note:

1. Water absorption, % = (Mass after immersion-Mass after drying and before immersion)/Mass after drying and before immersion×100
2. Test specimens were cut from the sample.

Test Photo:



During test

Before test

\*\*\*\*\* To be continued\*\*\*\*\*

# TEST REPORT

No. : XMIN190902311CCM

Date : Dec.03, 2019

Page: 7 of 11

## Annex E

### American Society for Testing and Materials -ASTM F 963-17(Clause 4.3.5) - total Lead in Substrate

#### Materials

Test Method: With reference to CPSC-CH-E1002-08.3. Analysis was performed by ICP-OES.

<u>Test Item(s)</u>	<u>Limit</u>	<u>Unit</u>	<u>MDL</u>	<u>001</u>
Total Lead (Pb)	100	mg/kg	20	ND
Comment				PASS

### American Society for Testing and Materials-ASTM F 963-17(Clause 4.3.5)-soluble heavy metal in Substrate Materials/paint and similar surface-coating materials

Test Method: With reference to ASTM F 963-17(Clause 8.3), analysis was performed by ICP-OES.

<u>Test Item(s)</u>	<u>Limit</u>	<u>Unit</u>	<u>MDL</u>	<u>001</u>
Soluble Lead (Pb)	90	mg/kg	5	ND
Soluble Antimony (Sb)	60	mg/kg	5	ND
Soluble Arsenic (As)	25	mg/kg	2.5	ND
Soluble Barium (Ba)	1000	mg/kg	10	ND
Soluble Cadmium (Cd)	75	mg/kg	5	ND
Soluble Chromium (Cr)	60	mg/kg	5	ND
Soluble Mercury (Hg)	60	mg/kg	5	ND
Soluble Selenium (Se)	500	mg/kg	10	ND
Comment				PASS

Notes: Results shown are of the adjusted analytical results

\*\*\*\*\* To be continued\*\*\*\*\*



# TEST REPORT

No. : XMIN190902311CCM

Date : Dec.03, 2019

Page: 8 of 11

## Asbestos

Test Method: With reference to NIOSH 9002:1994, Analysis was performed by PLM.

Test Item(s)	CAS NO.	Unit	MDL	001
Chrysotile	12001-29-5/132207-32-0	% (m/m)	0.1	Negative
Amosite	12172-73-5	% (m/m)	0.1	Negative
Crocidolite	12001-28-4	% (m/m)	0.1	Negative
Anthophyllite	77536-67-5	% (m/m)	0.1	Negative
Tremolite	77536-68-6	% (m/m)	0.1	Negative
Actinolite	77536-66-4	% (m/m)	0.1	Negative

### Notes:

- (1) Negative means the absence of asbestos, Positive means the presence of asbestos.
- (2) XRD will be used to confirm when the result is positive by PLM method.
- (3) 1 mg/kg = 0.0001%
- (4) MDL = Method Detection Limit
- (5) ND = Not Detected ( < MDL )
- (6) "-" = Not Regulated

\*\*\*\*\* To be continued\*\*\*\*\*



# TEST REPORT

No. : XMIN190902311CCM

Date : Dec.03, 2019

Page: 9 of 11

## Annex F

### Test Method:

With reference to ISO 16000-9:2006 / COR1-2007 & ISO 16000-6:2011 & ISO16000-3:2011.

Testing was performed by Environmental Chamber (50L), followed by sampling using Tenax-TA and DNPH tube, analysis using Thermodesorption System with Gas Chromatography Mass Spectrometry (TDS-GC/MS) and High Performance Liquid Chromatography-DAD (HPLC-DAD).

### Conclusion:

Based on the submitted sample(s) , test was performed according to Decree 2011-321 relative to the labeling of construction products, floor or wall coverings and paints and lacquers concerning their emission of volatile pollutants, sample is **A+** class.

### VOCs and Carbonyl Compounds:

	Compound Name	CAS No.	Result [mg/m <sup>3</sup> ]
			28 day
analysis result	Formaldehyde	50-00-0	ND
	Acetaldehyde	75-07-0	ND
	Toluene	108-88-3	ND
	Tetrachloroethylene	127-18-4	ND
	Xylene	108-38-3&106-42-3&95-47-6	ND
	1,2,4-Trimethylbenzene	95-63-6	ND
	1,4-Dichlorobenzene	106-46-7	ND
	Ethylbenzene	100-41-4	ND
	2-Butoxyethanol	111-76-2	ND
	Styrene	100-42-5	ND
	TVOC	-	0.017

Remark: 1. ND =not detectable (<MDL)  
 2. MDL = 0.002mg/m<sup>3</sup>  
 3. mg/m<sup>3</sup>= milligrams per cubic metre

\*\*\*\*\* To be continued\*\*\*\*\*



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: [CN.Doccheck@sgs.com](mailto:CN.Doccheck@sgs.com)

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765380 www.sgs.com.cn  
 中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765380 e [sgs.china@sgs.com](mailto:sgs.china@sgs.com)

# TEST REPORT

No. : XMIN190902311CCM

Date : Dec.03, 2019

Page: 10 of 11

**Evaluation according to Decree 2011-321 relative to the labeling of construction products, floor or wall coverings and paints and lacquers concerning their emission of volatile pollutants**

Classes	Calculated Result (µg/m³)	C	B	A	A+
Formaldehyde	ND	> 120	< 120	< 60	< 10
Acetaldehyde	ND	> 400	< 400	< 300	< 200
Toluene	ND	> 600	< 600	< 450	< 300
Tetrachloroethylene	ND	> 500	< 500	< 350	< 250
Xylene	ND	> 400	< 400	< 300	< 200
1,2,4-Trimethylbenzene	ND	> 2000	< 2000	< 1500	< 1000
1,4-Dichlorobenzene	ND	> 120	< 120	< 90	< 60
Ethylbenzene	ND	> 1500	< 1500	< 1000	< 750
2-Butoxyethanol	ND	> 2000	< 2000	< 1500	< 1000
Styrene	ND	> 500	< 500	< 350	< 250
TVOC	16.9	> 2000	< 2000	< 1500	< 1000

Remark: Calculated Result = SER / q

The concentrations of exposition are calculated in a conventional reference room of a total volume (V) of 30m³, in which is applied a rate of air renewal (n) of 0.5h<sup>-1</sup> and which dimensions are specified here below:

	Surface (S) (m²)	Load rate (L=S/V) (m²/m³)	Surface specific emission output (q=n/L) (m³.m <sup>-2</sup> .h <sup>-1</sup> )
Floor	12	0.4	1.25
Ceiling	12	0.4	1.25
One door	1.6	0.05	10
One window	2	0.07	7
Walls (minus door and window)	31.4	1	0.5
Joints (or very small surfaces)	0.2	0.007	70

\*\*\*\*\* To be continued\*\*\*\*\*



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: [CN.Doccheck@sgs.com](mailto:CN.Doccheck@sgs.com)

SGS-CSTC Inspection & Testing Services Co., Ltd.  
Xiamen Branch Testing Center (Authorized Constitutor Material Laboratory)

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765380 www.sgs.com.cn  
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765380 e [sgs.china@sgs.com](mailto:sgs.china@sgs.com)

## TEST REPORT

No. : XMIN190902311CCM


Date : Dec.03, 2019

Page: 11 of 11

### Test condition

Chamber Volume (m <sup>3</sup> )	0.05	Testing Temperature (°C)	23
Testing Humidity (rH%)	50	Air Exchange Rate (1/h)	0.5
Sample Loading (m <sup>2</sup> /m <sup>3</sup> )	0.4		
Tenax Sampling Flow (mL/min)	200	DNPH Sampling Flow (mL/min)	300
Tenax Sampling Time (min)	25	DNPH Sampling Time (min)	60
Tenax Sampling Volume (L)	5	DNPH Sampling Volume (L)	18

### Specimen photograph(s):



Original sample(s)

SGS authenticate the photo(s) on original report only

The test results are copied from report No.: XMIN190902310CCM dated:Nov.18,2019 issued by SGS

\*\*\*\*\*End of report\*\*\*\*\*



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Xi'an Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China  
Xiamen Branch Testing Center (China) Accredited for Material Laboratory

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765380 www.sgs.com.cn  
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765380 e sgs.china@sgs.com

## TEST REPORT

No. : XMIN191202902CCM

Date : Dec.04, 2019

Page : 1 of 2

CUSTOMER NAME: NEW OZ BMG AUSTRALIA  
ADDRESS: 262 PARRAMATTA ROAD GRANVILLE 2142 NSW AUSTRALIAN

Sample Name : STONE FLOOR  
Spec. : 8mm

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

\*\*\*\*\*

Test Required : Selected test(s) as requested by applicant  
Date of Receipt : Nov.22, 2019  
Testing Start Date : Nov.22, 2019  
Testing End Date : Nov.25, 2019  
Test Result(s) : For further details, please refer to the following page(s)  
(Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

\*\*\*\*\* To be continued\*\*\*\*\*

Signed for  
SGS-CSTC Standards Technical  
Services Co., Ltd. Xiamen Branch  
Testing Center



Civi Huang Authorized Signatory



SGS-CSTC Standards Technical Services Co., Ltd.  
Xiamen Branch Testing Center (China) Material Laboratory

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: [CN.Doccheck@sgs.com](mailto:CN.Doccheck@sgs.com)

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765380 www.sgs.com.cn  
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765380 e [sgs.china@sgs.com](mailto:sgs.china@sgs.com)

# TEST REPORT

No. : XMIN191202902CCM

Date : Dec.04, 2019

Page : 2 of 2

## Component analysis


Sample description: Panel (see photo)

Test Result(s):

No.	Parameter	Test method	Test results (%)
1	Silicon dioxide (SiO <sub>2</sub> )	BS EN ISO 12677:2011	0.67
2	Calcium oxide (CaO)		38.47
3	Chlorine (Cl)		17.92
4	Magnesium oxide (MgO)		5.80
5	Aluminium oxide (Al <sub>2</sub> O <sub>3</sub> )		0.25
6	Sodium oxide (Na <sub>2</sub> O)		0.10
7	Iron sesquioxide (Fe <sub>2</sub> O <sub>3</sub> )		0.08
8	Zinc oxide (ZnO)		0.08
8	Titanium dioxide (TiO <sub>2</sub> )		0.04
10	Potassium oxide (K <sub>2</sub> O)		0.03
11	Sulfur trioxide (SO <sub>3</sub> )		0.03
12	Loss on ignition (L.O.I)		36.53

Remark: The above test was carried out by HUAXIA CERAMIC TESTING CENTER.

## Sample Photo(s):



SGS authenticate the photo(s) on original report only

The test results are copied from report No.: XMIN191102781CCM dated: Dec.04,2019 issued by SGS

\*\*\*\*\*End of report\*\*\*\*\*



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-g-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Xi'an Xianghong Road, Xiang'an Torch Industrial Zone, Xi'an, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765380 www.sgs.com.cn  
Xiamen Geac Testing Center Xiamen Geac Testing Center Material Laboratory

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xi'an, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765380 www.sgs.com.cn  
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765380 e sgs.china@sgs.com